



SEGUIMIENTO PRODUCCION CAUCHO CAMPANA AK 125 FLEX



ESTANDARIZACION: 0014

MOLDE N° 0-048

LOTE N° **0042**

CARACTERISTICAS DE LA PIEZA		
PESO	24 gr	26 gr
DUREZA	70°+/-3° SHORE A	68° SHORE A
DENSIDAD	1.2+ 0.1 gr/cm ³	
DIMENSIONES S/P	CCF-001W	
MATERIAL	Formula M037	

ORDEN DE PEDIDO		
FECHA	O.C.	CANTIDAD
25/02/2010	5892	300
03/03/2010	5917	200
10/03/2010	5950	300

SUMINISTRO DE CAUCHO			
FECHA	O.C.	CANTIDAD P	CANTIDAD E
04/03/2010	202	100	
04/03/2010			39
15/03/2010			26
16/03/2010			13
17/03/2010			22
TOTAL			100

VULCANIZACION Y MOLDEO

MAQUINA	TIEMPO/TEMP	FECHA	CANTIDAD	OPERARIO	VERIFICACION PROCESO
Prensa N° 2	8Min/165°	03/03/2010	601	Fabian	Orlando Florez
Prensa N° 2	8Min/165°	04/03/2010	1104	Fabian	Orlando Florez
Prensa N° 2	8Min/165°	05/03/2010	635	Fabian	Orlando Florez
Prensa N° 2	8Min/165°	15/03/2010	121	Fabian	Orlando Florez
Prensa N° 2	8Min/165°	16/03/2010	994	Fabian	Orlando Florez
Prensa N° 2	8Min/165°	17/03/2010	316	Fabian	Orlando Florez

3771

ACABADO Y CONTROL CALIDAD

FECHA	NO CONFORME	VERIFICACION PROCESO
03/03/2010	7	Nora Lopez
03/03/2010	4	Nora Lopez
04/03/2010	7	Nora Lopez
04/03/2010	10	Nora Lopez
04/03/2010	6	Nora Lopez
05/03/2010	5	Nora Lopez
05/03/2010	7	Nora Lopez

OBSERVACIONES: